



Sierra Environmental Technologies, LLC.

GC IPAC

IMPREGNATED ACTIVATED CARBON

GC IPAC is a granular, coconut shell based activated carbon specially impregnated for the removal of ammonia from vapor streams. It is also available in other mesh sizes and as well as a coal based carbon as well.

Carbon Substrate

Mesh Size- 4 x 8, %:	90 (min.)
Less than No. 4, %:	5 (max.)
Greater than No. 8, %:	5 (max.)

CCl ₄ Activity, %:	60 (min)
Iodine Number, mg/g:	1000 (min)
Surface Area, m ² /g:	1000 (min)
Hardness, %:	95 (min)

Impregnated carbon

Bulk Density, lbs/cu. foot:	51
-----------------------------	----

Moisture, %:	12(max.)
--------------	----------

Head loss @ 50 fpm face velocity through a dense-packed bed, inches w.c./ft. of bed depth:	1.9 (max)
--	-----------

Ammonia Adsorption Efficiency,(until breakthrough),%:	95 (min.)
---	-----------

Media ph:	1-2
-----------	-----